

PU Round belts

| Shore Hardness 'A' Scale | Ultimate Tensile Strength PSI | Elongation % | Tear Strength | Compression Set at 25% Deformation % | Abrasion Resistance Cycles | Solenoid Brittle |
|--------------------------|-------------------------------|--------------|---------------|--------------------------------------|----------------------------|------------------|
| 85+2 | 5800 | 520 | 425 | 12 | 49 | -35 |

| Shore Hardness 'A' Scale | Ultimate Tensile Strength PSI | Elongation % | Tear Strength | Compression Set at 25% Deformation % | Abrasion Resistance Cycles | Solenoid Brittle |
|--------------------------|-------------------------------|--------------|---------------|--------------------------------------|----------------------------|------------------|
| ASTM D 2240 | ASTM D 412 | ASTM D 412 | PLI ASTM D412 | Taber e | ASTM D 745 | Point 0 C |
| 90+2 | 6400 | 500 | 600 | 6 | 309 | -35 |